

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - August 2024										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,440	2,061	2,636	27,777	17-9	18,0	8-9	
1.4307	304L	4307	2,440	2,061	2,636	27,777	18-8L	18,0	8-9	
1.4306	304L	4306	2,683	2,266	2,897	30,530	18-10L	18,0	10,0	
1.4541	321	4541	2,654	2,241	2,866	30,204	18-10Ti	17,0	9,0	
1.4401	316	4401	4,118	3,478	4,448	46,869	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	4,118	3,478	4,448	46,869	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	4,172	3,524	4,506	47,486	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,509	3,808	4,870	51,319	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,599	3,884	4,967	52,341	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,652	3,927	5,023	52,933	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	5,343	4,513	5,771	60,810	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,510	2,121	2,712	28,572	153MA™	18,5	9,5	
1.4845	310S	4845	4,316	3,644	4,661	49,114	25-20	25,0	20,0	
1.4833	309S	4833	3,241	2,737	3,499	36,882	23-13	22,0	12,5	
1.4835	S30815	253MA	2,838	2,397	3,066	32,304	253MA®	21,0	11,0	
1.4539	904L	904L	7,412	6,259	8,004	84,351	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	7,487	6,323	8,086	85,204	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	8,703	7,350	9,399	99,044	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,429	2,050	2,623	27,637	2304	23,0	4,5	
1.4462	S31803	2205	3,909	3,301	4,222	44,482	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,658	3,933	5,030	53,008	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,833	1,548	1,979	20,860	LDX2101®	21,0	1,5	
1.4828	-	4828	3,075	2,597	3,321	35,003	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,872	2,425	3,102	32,684	LDX2404™			
1.4003	S40977	4003	1,029	0,869	1,112	11,719	Ferritic			
1.4016	430	4016	1,168	0,987	1,263	13,302	Ferritic			
1.4509	441	4509	1,486	1,255	1,605	16,915	Ferritic			
1.4512	409	4512	0,984	0,831	1,063	11,203	Ferritic			
1.4521	444	4521	2,540	2,145	2,744	28,912	Ferritic			