

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - September 2024										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,317	1,969	2,528	26,831	17-9	18,0	8-9	
1.4307	304L	4307	2,317	1,969	2,528	26,831	18-8L	18,0	8-9	
1.4306	304L	4306	2,540	2,159	2,772	29,417	18-10L	18,0	10,0	
1.4541	321	4541	2,512	2,134	2,740	29,086	18-10Ti	17,0	9,0	
1.4401	316	4401	3,876	3,294	4,229	44,876	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,876	3,294	4,229	44,876	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	3,925	3,336	4,283	45,451	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,239	3,602	4,625	49,084	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,323	3,673	4,716	50,055	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,369	3,712	4,767	50,589	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	5,011	4,258	5,468	58,031	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,381	2,023	2,598	27,570	153MA™	18,5	9,5	
1.4845	310S	4845	4,049	3,442	4,418	46,892	25-20	25,0	20,0	
1.4833	309S	4833	3,060	2,600	3,340	35,436	23-13	22,0	12,5	
1.4835	S30815	253MA	2,689	2,285	2,934	31,135	253MA®	21,0	11,0	
1.4539	904L	904L	6,916	5,878	7,546	80,087	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	7,006	5,954	7,644	81,126	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	8,135	6,914	8,877	94,210	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,322	1,973	2,533	26,885	2304	23,0	4,5	
1.4462	S31803	2205	3,705	3,149	4,043	42,909	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,405	3,743	4,807	51,012	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,771	1,505	1,933	20,513	LDX2101®	21,0	1,5	
1.4828	-	4828	2,931	2,491	3,198	33,945	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,739	2,328	2,989	31,717	LDX2404™			
1.4003	S40977	4003	1,012	0,860	1,104	11,717	Ferritic			
1.4016	430	4016	1,153	0,980	1,258	13,356	Ferritic			
1.4509	441	4509	1,470	1,249	1,604	17,022	Ferritic			
1.4512	409	4512	0,972	0,826	1,060	11,252	Ferritic			
1.4521	444	4521	2,448	2,082	2,671	28,357	Ferritic			