

OSTP

AAF / Alloy Adjustment Factor

AAF for welded tubes and pipes - November 2024										
			Currency / Kgs				Old Ref			
EN	ASTM	OSTP	EUR	GBP	USD	SEK	GRADE	CR	NI	MO
1.4301	304	4301	2,409	2,014	2,655	27,321	17-9	18,0	8-9	
1.4307	304L	4307	2,409	2,014	2,655	27,321	18-8L	18,0	8-9	
1.4306	304L	4306	2,647	2,214	2,918	30,027	18-10L	18,0	10,0	
1.4541	321	4541	2,620	2,190	2,887	29,710	18-10Ti	17,0	9,0	
1.4401	316	4401	3,982	3,329	4,390	45,171	17-11-2	16,5	10,0	2,0
1.4404	316L	4404	3,982	3,329	4,390	45,171	17-11-2L	16,5	10,0	2,0
1.4571	316Ti	4571	4,035	3,374	4,447	45,769	17-11-2Ti	16,5	10,5	2,0
1.4436	316	4436	4,350	3,637	4,794	49,338	17-11-2.5	16,5	10,5	2,5
1.4432	316L	4432	4,430	3,704	4,882	50,241	17-12-2.5L	16,5	10,5	2,5
1.4435	316L	4435	4,491	3,755	4,950	50,932	17-13-2.5L	17,0	12,5	2,5
1.4438	317L	4438	5,146	4,302	5,672	58,365	18-13-3L	18,0	13,0	3,0
1.4818	S30415	153MA	2,482	2,075	2,735	28,141	153MA™	18,5	9,5	
1.4845	310S	4845	4,258	3,560	4,693	48,293	25-20	25,0	20,0	
1.4833	309S	4833	3,196	2,671	3,522	36,245	23-13	22,0	12,5	
1.4835	S30815	253MA	2,797	2,338	3,082	31,720	253MA®	21,0	11,0	
1.4539	904L	904L	7,153	5,980	7,882	81,119	904L	20,0	25,0	4,0
1.4547	S31254	254 SMO	7,148	5,977	7,879	81,075	254SMO®	20,0	18,0	6,0
1.4652	S32654	654 SMO	8,303	6,941	9,151	94,165	654 SMO®	24,0	22,0	7,3
1.4362	S32304	2304	2,363	1,976	2,605	26,804	2304	23,0	4,5	
1.4462	S31803	2205	3,734	3,122	4,115	42,349	2205	22,0	5,5	3,0
1.4410	S32750	2507	4,444	3,715	4,897	50,395	2507	25,0	7,0	4,0
1.4162	S32101	LDX2101	1,771	1,481	1,952	20,087	LDX2101®	21,0	1,5	
1.4828	-	4828	3,062	2,560	3,374	34,725	20-12Si	20,0	12,0	
1.4662	S82441	LDX2404	2,753	2,301	3,034	31,223	LDX2404™			
1.4003	S40977	4003	1,019	0,852	1,122	11,553	Ferritic			
1.4016	430	4016	1,149	0,960	1,266	13,028	Ferritic			
1.4509	441	4509	1,464	1,224	1,613	16,603	Ferritic			
1.4512	409	4512	0,972	0,813	1,071	11,023	Ferritic			
1.4521	444	4521	2,429	2,031	2,676	27,543	Ferritic			